

Blackhawk 5159

SELECTION & SPECIFICATION DATA

Fast Drying Asphalt Cutback Type

Blackhawk 5159 coating is used for many metal Description

corrosion and weather protection. Its high solids content gives it excellent coverage on marginally prepared metal and pavement surfaces, and it can also function as a primer for additional

bituminous coatings.

Uses · Pavement coating

Corrosion protection coating on steel substrates

• Primer for metal substrates

Color Black

Primer Self-priming

Consult ErgonArmor **Topcoats**

Finish Gloss

3 - 5 mils **Dry Film**

Thickness (DFT)

 $59\% \pm 2\%$ by weight **Solids Content**

Theoretical Coverage Rate 220 square feet per gallon at 4 mils DFT

<450g/L (3.75 lbs/gal) VOC Value(s)

SUBSTRATES & SURFACE PREPARATION

All All surfaces must be clean and free from debris

> and loose scale material or anything that may interfere with adhesion or act as a bond breaker

with the desired substrate.

MIXING & THINNING

Mixing No mixing required. Ready to use as is.

Do not thin. **Thinning**

APPLICATION EQUIPMENT GUIDELINES

Pump Size 15:1 or greater Airless Spray Hose Length: 20 ft x 1/2 in ID Single Leg or Pot

Apply with a wide fiber brush in order to create a Brush

smooth uniform film.

Roller Use a low nap phenolic core roller.

CLEANUP & SAFETY

Mineral spirits Cleanup

Safety Mixes and applications of this product present a

number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data

sheets before using.

Thorough air circulation must be used during Ventilation

> and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult

product SDS for further information.

PACKAGING, HANDLING & STORAGE

12 months at 75°F (24°C) when kept at **Shelf Life**

recommended storage conditions and in original

unopened containers.

40°F - 110°F (4°C - 43°C) Storage 0 – 100% relative humidity

Temperature &

Humidity

Storage

Store indoors. This product is not affected by excursions below these published storage temperatures, down to 10°F (-12°C), for a duration

of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and

homogeneous and properly mixed.

5 gallon (4.7 net fill) **Package Sizes**

55 gallon (53 net fill) & Shipping

350 gallon (340 net fill) carbon steel, returnable totes Weights

Bulk truckload

TYPICAL PHYSICAL PROPERTIES

Viscosity, at 77°F (25°C)	75 cps
Specific gravity, at 60°F (16°C)	26.2
Density, at 60°F (16°C)	7.472 lbs/gal

Rev 09/19

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.







