

SELECTION & SPECIFICATION DATA

Type	Premium Flashing Cement
Description	Blackhawk 5600 is an asbestos free, fiber-reinforced, premium asphalt roof cement suitable for trowel application to roofing and flashing. Blackhawk 5600 has excellent vertical slump resistance and exhibits a smooth consistency easily applied by the roofing professional.
Features	<ul style="list-style-type: none"> • Excellent vertical slump resistance • Smooth trowel consistency
Uses	<ul style="list-style-type: none"> • Construction of roof flashings • Vertical and horizontal applications
Color	Black
Solids Content	71% – 76% by volume
Theoretical Coverage Rate	14 square feet per gallon at 1/8 in thickness
VOC Value(s)	<350 g/l (2.92 lbs/gal)
Limitations	Not all APP membranes are alike and adhesion to these modified membranes should be tested. Do not use with membranes containing a burn off film.

SUBSTRATES & SURFACE PREPARATION

All	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

MIXING & THINNING

Mixing	No mixing required
Thinning	Do not thin

APPLICATION EQUIPMENT GUIDELINES

Trowel	Use bull nose roofing trowel.
---------------	-------------------------------

CLEANUP & SAFETY

Cleanup	Mineral spirits or equivalent solvent.
Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation

Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.

PACKAGING, HANDLING & STORAGE

Shelf Life	12 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
Package Sizes & Shipping Weight	43 lbs per 5 gallon pail Net contents 4.7 gallons
Storage Temperature & Humidity	40°F – 110°F (4°C – 43°C) 0 – 100% relative humidity
Storage	Store indoors. This product is not affected by excursions below published storage temperatures. Always inspect the product prior to use to make sure it is smooth and homogeneous.

PERFORMANCE DATA

Specifications	Category	Results
ASTM 4586	Type II	Pass

Rev 06/19

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.