



## SELECTION & SPECIFICATION DATA

<b>Type</b>	Non-fibered Asphalt Emulsion Concrete Primer
<b>Description</b>	Blackhawk 7010 Roof Primer is a water-based, asphalt roof primer for concrete substrates. It is designed to provide excellent surface conditions for hot-applied asphaltic membranes.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Extremely low VOCs</li> <li>• Single-component</li> <li>• Cold-applied</li> </ul>
<b>Uses</b>	Concrete primer for asphalt roofing
<b>Color</b>	Brown applied, dries black
<b>Theoretical Coverage Rate</b>	300 – 400 square feet per gallon depending on surface porosity
<b>VOC Value(s)</b>	<10 g/L (0.09 lbs/gal)
<b>Limitations</b>	Protect from freezing. Not for immersion service.

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	Surfaces must be clean and dry. Remove all dirt, dust, oil and other contaminants.
------------	--

## MIXING & THINNING

<b>Mixing</b>	Mix before application to ensure consistency
<b>Thinning</b>	Do not thin

## APPLICATION EQUIPMENT GUIDELINES

<b>Brush</b>	Wide, fiber brush
<b>Roller</b>	Low-nap phenolic core roller

## CLEANUP & SAFETY

<b>Cleanup</b>	Wet product can be cleaned up using water. Dried material may be cleaned using mineral spirits or an equivalent solvent.
<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Use in well ventilated areas

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	6 months when kept at recommended storage conditions of around 75°F (24°C) and in original unopened containers.
<b>Package Sizes &amp; Shipping Weights</b>	5 gallon pail - 52 lbs (24 kg) 55 gallon drum - 590 lbs (268 kg) 275 gallon tote - 3150 lbs (1429 kg)
<b>Storage Temperature &amp; Humidity</b>	40°F – 110°F (4°C – 43°C) 0 – 100% relative humidity Protect from freezing
<b>Storage</b>	Store Indoors. Always inspect the product prior to use to ensure proper uniformity.

## TYPICAL PHYSICAL PROPERTIES

Density	8.2 lbs/gal
Solids, by volume	30%
Dry time, at 75°F (25°C)	1 hour or less

Rev 07/19

### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).

