

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Fibered Asphalt Emulsion
<b>Description</b>	A trowel-able fibrated blend of selected mineral fillers and emulsified asphalts that provides excellent protection against moisture vapor intrusion in porous substrates such as cement.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Water-based with low VOCs</li> <li>• Very stable - resists separating</li> <li>• Environmentally friendly</li> <li>• Worker friendly</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Dampproofing</li> <li>• Adhesive for polystyrene insulation</li> <li>• Moisture barrier</li> </ul>
<b>Color</b>	Black
<b>Finish</b>	Matte
<b>Primer</b>	Self-priming
<b>Dry Film Thickness (DFT)</b>	3 – 60 mils per coat
<b>Solids Content</b>	50% by weight 50% by volume
<b>Theoretical Coverage Rate</b>	802 square feet per gallon at 1 mil DFT
<b>Maximum Dry Temperature Resistance</b>	300°F (149°C)
<b>Limitations</b>	Protect from freezing Not for immersion service

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	Surfaces must be clean and dry. Remove all dirt, dust, oil and all other contaminants.
<b>Previously Painted Surfaces</b>	Consult with ErgonArmor Technical Service Department.

## MIXING & THINNING

<b>Mixing</b>	Not required
<b>Thinning</b>	Generally not required. Product is thixotropic and will thin under shear. If a reduction in static viscosity is desired, agitate to thin. The addition of water is not recommended.

**Ratio** Single component

## APPLICATION GUIDELINES

<b>Application Guide</b>	Ertech 2120 is designed to be trowel or glove applied.
<b>Film Thickness</b>	A film thickness of up to 120 mils wet can be achieved on vertical surfaces without sagging.
<b>Temperature</b>	Use in temperatures of 50°F (10°C) or higher for best performance.
<b>Dry-To-Touch</b>	2 – 4 hours at 77°F (25°C). Dry times are decreased with air movement over the coating.
<b>Full Cure</b>	24 – 48 hours at 77°F (25°C). Cure times are decreased with air movement over the coating.

## CLEANUP & SAFETY

<b>Cleanup</b>	Tools and hands should be cleaned with soap and water before the emulsion sets. Dried material can be cleaned with mineral spirits. Spray equipment should be flushed with soapy water then fresh water for short periods of non-use. For longer periods of non-use, a final flush using mineral spirits is recommended.
<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Use in well ventilated areas.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	6 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
<b>Package Sizes &amp; Shipping Weights</b>	5 gallon pail – 44 lbs (20 kg) 16 gallon keg – 141 lbs (64 kg) 53 gallon drum – 475 lbs (215 kg)
<b>Storage Temperature</b>	50°F – 110°F (10°C – 43°C)
<b>Storage</b>	Protect from freezing. Do not store product outside. Store indoors.

### TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.2 lbs/gal
Solids by weight ASTM D5201-05a	50%
Solids by volume ASTM D5201-05a	50%
Specific gravity	0.98
Dry-to-touch, 77°F (25°C) ASTM D5895-96	2 – 4 hours
Full cure, 77°F (25°C)	24 – 48 hours
Viscosity, 77°F (25°C), brass cone pen ASTM D2983-19	360 dmm
Resistance to oils, greases & solvents	Poor
VOC ASTM D3960-05	0.2 lbs/gal max

Rev 01/2020

#### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).