

SELECTION & SPECIFICATION DATA

Type	Novolac Epoxy
Description	Novocoat SC6300 is a two-component, 100% solids, novolac epoxy coating system, engineered for extreme temperature and corrosive conditions.
Features	<ul style="list-style-type: none"> • Excellent chemical resistance to wide range of acids and caustics • Low permeation rate for tank lining service • Solvent free – 100% solids
Uses	<ul style="list-style-type: none"> • Pipe wraps • Secondary containment areas • Chemical process equipment supports and pads • Heat exchangers and tube sheets • Internal bulk storage tank, pipe and vessel lining
Color	Clear
Finish	Gloss
Dry Film Thickness (DFT)	2 or 3 coats at 8 or 12 mils each 3 or 4 coats at 8 or 12 mils each for high temperatures or severe chemical service
Solids Content	99 – 100% by volume

SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants.
Steel	<p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 – 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 3 Commercial Blast with angular profile of 1.5 – 3.0 mils, SSPC-SP 2 Hand Tool or SSPC-SP 3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>
Previously Painted Surfaces	Consult with ErgonArmor Technical Service.

MIXING & THINNING

Ratio	3A:1B by volume
Mixing	Except for plural spray applications, do not mix partial kits. Power mix parts A and B separately then combine and power mix.
Thinning	<p>Spray: Up to 6.5 oz/gal (5%) with Novocoat TH1710 Thinner</p> <p>Brush: Up to 8 oz/gal (6%) with Novocoat TH1710 Thinner</p> <p>Roller: Up to 8 oz/gal (6%) with Novocoat TH1710 Thinner</p>
Pot Life	30 minutes at 75°F (24°C)
	Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.

Cleanup MEK or Acetone

APPLICATION GUIDANCE

Spray Application	The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.
Airless Spray Plural Component	<p>Tip Size: 0.015-inch to 0.025-inch, reversible type</p> <p>Part A Fluid Line: 1/2-inch ID</p> <p>Part B Fluid Line: 3/8-inch ID</p> <p>Spray Line: 1/2-inch ID x 50 feet maximum</p> <p>Whip: 1/4 to 3/8-inch ID x 20 feet maximum</p> <p>Pump Size: 56:1 or greater</p> <p>Output: 1,500 – 3,500 psi</p> <p>Static Mixer: 2 x 1/2-inch ID x 12 inches (24-inch total length) behind mixing valve</p> <p>Part A Temperature: 115°F – 125°F (46°C – 52°C)</p> <p>Part B Temperature: 90°F – 95°F (32°C – 35°C)</p>
Airless Spray Single Leg or Hot Pot	<p>Pump Size: 56:1 or greater</p> <p>Hose: 3/8-inch ID minimum x 50 feet maximum</p> <p>Whip: 10 ft x 1/4-inch to 3/8-inch ID (minimum)</p> <p>Tip Size: 0.027-inch – 0.029-inch</p> <p>Output: 5600 to 7000 psi, filter removed</p>
Brush & Roller	Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 75°F (24°C).
Brush	Medium bristle brush.
Roller	Short-nap synthetic roller cover with phenolic core.

CURE SCHEDULE & RECOAT WINDOW

TEMPERATURE	MINIMUM RECOAT	MAXIMUM RECOAT	RETURN TO SERVICE (AQUEOUS/HYDROCARBON IMMERSION)
50°F (10°C)	3 hours	12 hours	7 days
77°F (25°C)	1.5 hours	6 hours	7 days
140°F (60°C)	10 minutes	Not recommended	4 hours
Dry-to-touch: 4 hours at 77°F (25°C)			

Return-to-service varies with chemical exposure. Consult ErgonArmor Technical Service for guidance.

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

PACKAGING, ESTIMATING & HANDLING

Package Sizes	Clear, 0.89 gal (3.4 L) Kit - Part A Resin, 0.65 gal (2.5 L) Pail - Part B Hardener, 0.24 gal (0.9 L) Bottle Item #: M-SC6300-1GLKT-01
Theoretical Coverage	200 square feet per gallon at 8 mils 133 square feet per gallon at 12 mils Allow for loss in mixing and application.
Storage & Shelf Life	Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	SYSTEM	VALUE
Dry adhesion ASTM D4541	Blasted steel 1 coat	>3,000 psi (21 MPa)
Wet adhesion ASTM D4541 5 days 158°F (70°C) water	Blasted steel 1 coat	>2,500 psi (17 MPa)
Abrasion ASTM D4060	1000 cycles, CS17 wheel 1000 gm load	<40 mg
Compressive strength ASTM C109		11,000 – 14,000 psi (75 – 96 MPa)
Hardness ASTM D2240	Blasted steel 1 coat	84 Shore D

SERVICE TEMPERATURE

SERVICE	MAXIMUM TEMPERATURE
Dry, continuous	450°F (232°C)
Dry, non-Continuous	550°F (288°C)
Under insulation	300°F (149°C)

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

Discoloration and loss of gloss occur above 200°F (93°C) but do not affect performance.

Rev 03/2021

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.