

SELECTION & SPECIFICATION DATA

Type	Epoxy tile adhesive
Description	Thinset Adhesive is a 100% solids 3 component tile and floor paver adhesive.
Uses	<ul style="list-style-type: none"> • Dairies, bakeries, breweries and distilleries • Meat and poultry processing plants • Pharmaceutical plants • Chemical process facilities • Bonds steel floor plate to concrete • Adhesive for pressure-embedded Tufchem™ Tiling Systems
Features	<ul style="list-style-type: none"> • Exceeds ANSI A118.3 requirements • Economical - narrowest practical thickness may be used • Excellent resistance to moderate acids, alkalis, and solvents • Easy-to-spread, creamy consistency • Pre-portioned for easy on-the-job mixing • Good resistance to thermal shock • Good tolerance for damp surfaces • Low odor - ideal for repairs to operating plants • Alternative hardener available for low temperature application conditions
Limitations	<ul style="list-style-type: none"> • Not suitable for vertical wall tile applications. Consult with ErgonArmor for wall tile applications. • Not for use beyond its chemical resistance or thermal capabilities. Consult ErgonArmor with specific questions.

INSTALLATION GUIDANCE

Reference Specifications	CES-309 Installation of direct bond tile floors CES-311 Installation of Tufchem Tiling Systems	
Installation Conditions	Thinset Adhesive is formulated for ideal handling at 70°F (21°C). Bring bricks, tiles, adhesive components, substrate, and air to the same temperature. Do not use when air and substrate temperatures are below 50°F (10°C) or greater than 90°F (32°C). Bricks or tiles must be clean, dry and neutral pH.	
Ratio	1.0 resin: 0.27 hardener: 3.43 filler by weight 3 resin: 1 hardener by volume (liquids only)	
Mixing	Pour measured quantity of Resin into clean, dry mixing vessel. Slowly add measured quantity of Hardener to Resin and mix thoroughly. After liquids are mixed completely, add Filler and mix until Filler is thoroughly wetted and adhesive is creamy, free of lumps and trowelable.	
Work Life	60 minutes at 70°F (21°C). Work life is shorter at higher temperatures. A larger volume of mixed material will have a shorter work life than a smaller volume.	
Cleanup	Xylene or MEK	
<u>CURE TIME</u>		
Brick/Tile Temperature	Initial Set	Full Cure
70°F (21°C)	4.5 hours	<7 days per ANSI A118.3
<u>SAFETY</u>		
Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.	
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.	

PACKAGING & ESTIMATING

Product	Code	Packaging
Thinset Resin	19673	4 x 7.0 lb (0.75 gal) can case
	29433	42 lb (4.5 gal) pail
	29581	471 lb (51 gal) drum
Thinset Hardener	19674	4 x 1.9 lb (0.25 gal) can case
	29434	11.4 lb (1.5 gal) can
	29582	382 lb (47 gal) drum
Thinset Filler	19697	48 lb (21.8 kg) bag

Theoretical Coverage

A 132 lb unit consists of 1 case resin, 1 case hardener, and 2 x 48 lb bags filler and will cover 140 sf (13 m²) at 3/32-1/8 inch (2.4-3.2 mm) thickness.

A 198 lb unit consists of 1 x 42 lb pail resin, 1 x 11.4 lb can hardener, and 3 x 48 lb bags filler and will cover 210 sf (19.5 m²) at 3/32-1/8 inch (2.4-3.2 mm) thickness.

A 6,595 lb unit consists of 3 x 471 lb drums resin, 1 x 382 lb drum hardener, and 100 x 48 lb bags filler and will cover 7,000 sf (650 m²) at 3/32-1/8 inch (2.4-3.2 mm) thickness.

Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	Gray
Density, ASTM C138	110 lb/ft ³ (1629 kg/m ³)
Compressive strength, ANSI A118.3 test 5.6, 7-day	>10,000 psi (69 MPa)
Bond to Tile, ANSI A118.3 test 5.5	>2,000 psi (13.8 MPa)
Adhesion to concrete	Exceeds tensile strength of concrete
Thermal shock resistance, ANSI A118.3 test 5.8	>500 psi (3.4 MPa)
Tensile strength, ANSI A118.3 test 5.7	>2,000 psi (13.8 MPa)
Flexural strength, ASTM C453	>4,500 psi (31 MPa)

Rev 06/2020
TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.